

AMENDMENTS TO THE SPECIFICATION:

Please amend the paragraph at page 8, line 19, as follows:

Each resin composition obtained was preformed under pressure of ~~700MPa~~
70MPa or 700 kg/cm² and then sintered at 370°C for three hours to obtain a cylinder-
shaped molded article of a diameter of 50mm height of 100mm.